AD-A271 147 - KEEP THIS COPY FOR REPRODUCTION PURPOSES ATION PAGE **Orm 400100000

OME NO 0704 0188

AGENCY USE ONLY LEAVE DIADE

2 REPORT DATE 7/31/93

3 REPORT TYPE AND DATES COVERED

01/01/93 - 05/31/93 FINAL REPORT

A TITLE AND SUBTITLE

Single Source Precursors for the OMCVD of III/V Compound Semiconductors

DAAL03-89-K-0164

S. FUNDING NUMBERS

6. AUTHORIS

Dr. Richard A. Jones & Dr. John G. Ekerdt

7 PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES)

The University of Texas at Austin Department of Chemistry & Biochemistry Welch Hall 4.416

Austin, TX 78712

PERFORMING ORGANIZATION REPORT NUMBER

9. SPONSORING MONITORING AGENCY NAME(S) AND ADDRESS(ES)

U.S. Army Research Office

P. O. Box 12211

Research Triangle Park, NC 27709-2211

IO. SPONSORING MONITORING AGENCY REPORT NUMBER

11. SUPPLEMENTARY NOTES

The views, opinions and/or findings contained in this report are those of the author(s) and should not be construed as an official Department of the Army position, policy, or decision, unless so designated by other documentation.

124 DISTRIBUTION AVAILABILITY STATEMENT

125. DISTRIBUTION COM

Approved for public release; distribution unlimited.

3. ABSTRACT (Maximum 200 words)

The overall goals are to develop the fundamental chemistry of group III and group V compounds in several key areas. The underlying rationale is that we may be able to ultimately improve on the preparation and properties of important materials used in the semiconductor industries. The research comprises a collaboration between a synthetic inorganic chemist and a chemical engineer. The three main areas are (1) single source precursors for OMCVD of III/V semiconductors, (2) alternative precursors for OMCVD studies, group III or V hydrides, and (3) the organometallic chemistry of bismuth. The first area will employ compounds of the general type $[R_2M(\mu-R'_2E)]_2$ (M=Al, Ga,In; E=P,As; R,R'=alkyl,aryl,etc.) and the second will employ similar compounds but with R or R' replaced by the hydride ligand. We will explore the relationships between precursor structures, mechanisms of decomposition and thin film formation, and the morphological and electrical properties of the grown films. In the third area we will explore the organometallic chemistry of bismuth and compounds which may serve as precursors to important materials such as InBiSb.

14. SUBJECT TERMS

OMCVD, precursors, thin film formation, organometallic.

15. NUMBER OF PAGES

TE. MUCE COOL

SECURITY CLASSIFICATION UNCLASSIFIED

1 18. SECURITY CLASSIFICATION OF THIS PAGE UNCLASSIFIED

119. SECURITY CLASSIFICATION OF ABSTRACT UNCLASSIFIED

28. LIMITATION OF ASSTRACT

UL

-8-

Standard form 296 (Rev 2-00) Prostries by ANS: 100 239-18

NSN 7540-01-280-5500

MASTER COPY PLEASE KEEP THIS "MEMORANDUM OF TRANSMITTAL" BLANK POR REPRODUCTION PURPOSES WHEN REPORTS ARE GENERATED UNDER ARO SPONSORSHIP, PORWARD A COMPLETED COPY OF THIS FORM WITH EACH REPORT SHIPMENT TO THE ARO. THIS WILL ASSURE PROPER IDENTIFICATION. NOT TO BE USED FOR TECHNICAL PROGRESS REPORTS; SEE PAGE 4 PARA (5) FOR PROGRESS REPORT INSTRUCTIONS.

MENORANDUN OF TRANSMITTAL

U.S. Army Research Office ATTN: AMXRO-RT-IPL P.O. Box 12211 Research Triangle Park, NC 27709-2211

Reprint (15 copies) Technical Report (50 copies)	
Manuscript (1 copy) X Final Report (50 copies)	
Thesis (1 copy)	-
MS PhD Other	
CONTRACT/GRANT NUMBER DAAL03-89-K-0164	
TITLE: Single Source Precursors for the OMCVD of III/V Compound Semiconduct	ors
is forwarded for your information. SUBMITTED FOR PUBLICATION TO (applicable only if report is manuscript):	

Sincerely,

Dr. Richard A. Jones 26748-CH
Dr. John G. Ekerdt DAAL03-89-K-0164
Department of Chemistry & Biochemistry
University of Texas
Austin, TX 78712

1 MAY 1993

Single Source Precursors for the OMCVD of III/V Compound Semiconductors

FINAL REPORT
Richard A. Jones and John G. Ekerdt

1 January 1993 - 31 May 1993

U. S. ARMY RESEARCH OFFICE 26748-CH DAAL03-89-K-0164

The University of Texas at Austin

APPROVED FOR PUBLIC RELEASE;
DISTRIBUTION UNLIMITED.

A. STATEMENT OF PROBLEM STUDIED

Single Source Precursors for the OMCVD of III/V Compound Semiconductors

The overall goals are to develop the fundamental chemistry of group III and group V compounds in several key areas. The underlying rationale is that we may be able to ultimately improve on the preparation and properties of important materials used in the semiconductor industries. The research comprises a collaboration between a synthetic inorganic chemist and a chemical engineer. The three main areas are (1) single source precursors for OMCVD of III/V semiconductors, (2) alternative precursors for OMCVD studies, group III or V hydrides, and (3) the organometallic chemistry of bismuth. The first area will employ compounds of the general type $[R_2M(\mu-R'_2E)]_2$ (M=Al, Ga,In; E=P,As; R,R'=alkyl,aryl,etc.) and the second will employ similar compounds but with R or R' replaced by the hydride ligand. We will explore the relationships between precursor structures, mechanisms of decomposition and thin film formation, and the morphological and electrical properties of the grown films. In the third area we will explore the organometallic chemistry of bismuth and compounds which may serve as precursors to important materials such as InBiSb.

B. SUMMARY OF IMPORTANT RESULTS

The technical details of the research results are more fully documented in the publication and technical reports previously filed during the period of this research. Our initial experiments focused on the decomposition pathways of the dinuclear GaAs precursors [Me₂ Ga(μ -t-Bu₂As)]₂ (1), [Et₂ Ga(μ -t-Bu₂As)]₂ (2), [Me₂ Ga(μ -i-Pr₂As)]₃ (3), and [Me₂ Ga(μ -Me₂As)]₃ (4).

Two reactor systems have been used. The initial pyrolysis experiments were conducted in a low pressure system (<10⁻⁴Torr) in order to reproduce the conditions under which GaAs films are deposited. The pyrolysis system consists of a quartz tube through which the precursors flow. The temperature of the pyrolysis zone is increased linearly with time. Reactions are monitored by feeding the reactor effluent directly into an HP 5970B Mass EI mass spectrometer which was modified to accommodate the large gas load. The results indicate that for the dimeric precursors, 1 and 2, the 1:1 Ga:As stoichiometry present in the precursor remains intact until the molecule decomposes to form GaAs on a heated surface. Trimeric precursors, 3 and 4, appear, however, to lose their stoichiometry by reacting to form diarsines, Me₄As₂ for example from 4, at temperatures as low as 150°C. One possible explanation for diarsine formation from trimers and not dimers could be associated with the possibility of forming a stable product from the trimer, such as [R₂Ga]₃As. A related compound, [(thf)Br₂Ga]₃As, has been reported in the literature [R.L. Wells, S. Shafieezad, A. T. McPhail and C. G. Pitt, J. Chem. Soc., Chem. Commun., 1823 (1987)] and forms the basis for our explanation. A trigallium-arsine compound cannot form from a single dimer and this may explain the lack of diarsine formation from the dimers. The pyrolysis results indicate the t-Bu ligands begin to be eliminated from the As atoms at 325°C and reaction is complete by 450°C. The i-Pr ligands are slightly more thermally stable with reaction beginning at 375°C and with complete elimination occurring by 500°C. Methyl ligands appear to be eliminated from the Ga atoms between 400 and 500°C. Ethyl ligands are more thermally labile with elimination occurring from 325 to 450°C. The other reactor system, which was constructed during the period of the grant, is designed for chemical beam epitaxy. The system features a load lock/preparation chamber and a main deposition chamber each of which are pumped by turbomolecular pumps. A mass spectrometer has been fitted to the deposition chamber in order to insure that conditions are kept constant throughout a

growth of GaAs has finally been achieved on (100) GaAs substrates using compounds 1 and 2. The key to achieving epitaxy appears to lie in operating the reactor at pressures no greater than 10⁻⁵ Torr and at temperatures of 400°C and above. At higher pressures there is apparently still enough gas phase reaction and nucleation for the films to become polycrystalline. Photoluminescence spectra of films grown from 1 at 500°C indicate the presence of both silicon and carbon as impurities. ICP-MS analysis of the starting material shows high concentrations of Si which probably arise from stopcock grease used in the synthesis. Steps are being taken to eliminate this source of contamination. The carbon, however, probably originates from the methyl ligands of the precursor.

Since the binary (homoleptic) compounds of general formula $(R_2E)_3M$ (M = Al,Ga,In; E = P,As; R = t-Bu, i-Pr) contain no M-carbon bonds we considered them to be possible precursors for the ME materials despite the apparently unfavorable 1:3, M:E ratio. They have proven to be surprisingly versatile as OMCVD precursors. We believe that this may be due to the fact that they contain no metal-carbon bonds and the mechanistic pathway for decomposition involves the expulsion of the small stable molecule R_2E -E R_2 .

i.e.
$$(R_2E)_3M \rightarrow "R_2E-M" + R_2E-ER$$

The R₂E-M fragment then decomposes to ME. Thus $(t\text{-Bu}_2\text{As})_3\text{Ga}$ gives epitaxial layers of GaAs at 525°C, 5 x 10⁻⁵ Torr pressure. The low temperature (77 K) photoluminescent spectra indicate that the material is n-type and has 1500 cm²/V.sec. mobility.

Several other classes of compounds have been evaluated for film growth. These include a base free diphosphadigalletane [Ar'PGa-t-Bu]₂ Ar'=(2,4,6-t-Bu₃-C₆H₂); aluminum based compounds which feature PH₂ or AsH₂ units [t-Bu₂Al (EH₂)]₃ (E=P,As); μ -t-BuPH and μ -t-BuAsH bridged dimers [t-Bu₂Ga(μ -t-BuPH)]₂ and [t-Bu₂Ga(μ -t-BuAsH)]₂ as well as cubanes of the type [ϕ ₃SiEM-t-Bu]₄ (M=Al,Ga).

Other studies have continued to focus on various aspects of the decomposition pathways for compounds featuring group 13/15 elements. In particular the cyclic trimeric hydroxy, amido. phosphido and arsenido derivatives of aluminum and gallium of general formula [t-Bu₂Al(μ -X]₃ (X = EH₂; E = N,P, As; X = OH, OD) have been isolated and fully characterized. The use of these compounds as single source precursors to the appropriate solid state semiconductor material is currently under investigation.

Other studies have focused on precursors to gallium nitride (GaN). This is particularly difficult to grow thin films of partly because of the volatility of nitrogen. We have isolated and characterized both primary amide and amine complexes of both gallium and indium and structurally characterized the complexes [Me₂Ga(μ -NH-t-Bu)]₂, Me₃Ga.NH₂-t-Bu and Me₃In.NH-t-Bu). Again, these compounds as well as the alkylamidogallates Li(THF)₂(μ -NH-t-Bu)₂GaCy₂ and MgCl(THF)₂(μ -3,5-Me₂Pz)₂GaCy₂ may prove to be viable single source precursors. Of particular interest is the X-ray structure of Cy₂GaBrNH₂Ph which contains a close Ga••H-N (agostic) interaction. This may well represent a model of the way in which alkane is eliminated from the reaction of a trialkyl gallium species with an amine to give either a gallium amide R₃Ga + H₂NR \rightarrow R₂Ga-NHR

or finally gallium nitride itself.

Finally, examples of a novel class of monomeric precursor which features M-H bonds have been isolated and characterized. Examples include H₂AlP(Mesityl)₂•NM₃ and H₂AlAs(Mesityl)₂•NMe₃.

C. LIST OF MANUSCRIPTS PUBLISHED UNDER ARO SPONSORSHIP

- 1. Preparation of Indium Antimonide Using a Single-Source Precursor"; A. H. Cowley, R. A. Jones, C. M. Nunn and D. L. Westmoreland, *Chem. Mats.* (1990) 221-222.
- 2. "III/V Precursor Clusters with P-H or As-H Bonds. A Low Temperature Route to Gallium Arsenide and Gallium Phosphide"; A. A. Cowley, P. R. Harris, R. A. Jones and C. M. Nunn, *Organometallics*, 1991, 10, 652-656.
- 3. "Isopropylphosphido and Arsenido Derivatives of Gallium and Indium. Isolation of Gallium-Phosphorus and Indium-Phosphorus Dimers and Trimers"; A. H. Cowley, R. A. Jones, M. A. Mardones and C. M. Nunn, *Organometallics*, 1991, 10, 1635-1637.
- 4. Reaction of (t-BuGaCl₂)₂ with Ar'PHLi (Ar' = 2,4,6-t-Bu₃C₆H₂): Preparation of the Chloride-Bridged Dimer (t-BuGa(Cl)P(H)Ar')₂"; A. H. Cowley, R. A. Jones, M. A. Mardones, J. L. Atwood and S. G. Bott, *Hetroatom*, 1991, 2. 11-15.
- 5. "Primary Amido and Amine Adduct Complexes of Gallium: Synthesis and Structures of [t-Bu₂Ga(μ-NHPh)]₂ and t-Bu₃Ga•NH₂Ph"; D. A. Atwood, R. A. Jones, A. H. Cowley, S. G. Bott and J. L. Atwood *Polyhedron*, 1991, 10, 1897-1902.
- 6. "Tetrameric Gallium and Aluminum Chalcogenides, [tBuME]4 (M = Al, Ga; E = S, Se, Te). A New Class of Cubane"; A. H. Cowley, R. A. Jones, P. R. Harris, D. A. Atwood, Leopoldo Contreras and C. J. Burek Angew. Chem. Int. Ed. Engl., 1991, 30, 1143-1145.
- 7. "A Novel Gallium-Phosphorus Cage Compound" A. H. Cowley, R. A. Jones, M. A. Mardones, J. L. Atwood and S. G. Bott Angew. Chem. Int. Ed. Eng., 1991, 30, 1141-1143.
- 8. "Synthesis and Structure of the First Base-Free Diphosphadigalletane" D. A. Atwood, A. H. Cowley, R. A. Jones and M. A. Mardones J. Amer. Chem. Soc., 1991, 113, 7050-7052.
- 9. "Single Source Precursors for III-V OMCVD Growth and Pyrolysis Studies" R. A. Jones, A. H. Cowley and J. G. Ekerdt *Mats. Res. Soc. Symp. Proc.*, 1991, 204, 73-82.
- 10. "Synthesis and Structures of Two Bulky Gallium Chlorides," D. A. Atwood, A. H. Cowley, R. A. Jones, Miguel A. Mardones, J. L. Atwood and S. G. Bott, J. Coord. Chem. 1992, 25, 233.
- 11. "Pyrolysis Studies of the Single-Source GaAs Precursors [Me₂Ga(μ -*i*-Pr₂As)]₃, [Me₂Ga(μ -Me₂As)]₃, [Me₂Ga(μ -*t*-Bu₂As)]₂, and [Et₂Ga(μ -*t*-Bu₂As)]₂," J. E.

- Miller, M. A. Mardones, J. W. Nail, A. H. Cowley, R. A. Jones and J. G. Ekerdt, Chem. of Mats. 1992, 4, 447.
- 12. "Insertion of LiPEt₂ into Poly(dimethylsiloxane) to Give [LiOSiMe₂PEt₂]₆," S. G. Bott, R. A. Jones and S. U. Koschmieder, J. Chem. Soc., Chem. Comm. 1992, 9, 726-727.
- 13. "Growth of Epitaxial (100) GaAs Films Using the Single-Source Precursor [Me₂Ga(μ-t-Bu₂As)]₂", J. E. Miller and John G. Ekerdt, *Chem. of Mats.* 1992, 4, No. 1, 7-9.
- 14. "Unusual intramolecular hydrogen bonding in Cy₂GaBrNH₂Ph. The first structurally characterized dialkyl gallium halide primary amine adduct," D. A. Atwood, A. H. Cowley and R. A. Jones, *J. Organomet. Chem.* **1992**, 430, C29-C32.
- 15. "Primary Amide and Amine Complexes of Gallium and Indium: X-ray Crystal Structures of [Me₂Ga(μ-NH(t-Bu))]₂, Me₃Ga•NH₂(t-Bu) and Me₃In•NH₂(t-Bu),"
 D. A. Atwood, A.H. Cowley, R. A. Jones, J. L. Atwood and S. G. Bott, J. Organomet. Chem. 1992, 434, 143-150.
- 16. "Structural Characterization of a Dialkylgallium Cation: X-ray Crystal Structure of [Me₂Ga(t-BuNH₂)₂]Br," D. A. Atwood, R. A. Jones, A. H. Cowley S. G. Bott and J. L. Atwood, J. Organomet. Chem. 1992, 425, C1.
- 17. "Synthesis and Structural Characterization of o-Tol₃Ga•OEt₂" D. A. Atwood, A. H. Cowley and R. A. Jones, J. Coord. Chem. 1992, 26, 69.
- 18. "Synthesis and X-ray Structure of Me₂InI(NH₂(t-Bu)): The First Structurally Characterized Amine Adduct of a Dialkyl Indium Iodide," D. A. Atwood, A. H. Cowley, R. A. Jones, J. L. Atwood and S. G. Bott, J. Coord. Chem. Accepted.
- 19. "Phosphorus Atoms in Unusual Environments," A. H. Cowley, R. A. Jones and M. A. Mardones, A. C. S. Symposium Series. 1992, No. 486, Chapter 4.
- "Chemical Beam Epitaxy of GaAs Films Using Single-Source Precursors," J. G. Ekerdt, M. S. Jackson, V. Lakhotia, K. A. Pacheco, Y. M. Sun, A. H. Cowley, R. A. Jones and S. U. Koschmieder, J. Crystal. Growth 1992, 124, 158-164.
- 21. "Synthesis of the First Diarsadigalletane," D. A. Atwood, A. H. Cowley, R. A. Jones and M. A. Mardones, J. Organomet. Chem. 1992, 439, C33-C35.
- *22. "Cyclic Trimeric Hydroxy, Amido, Phosphido and Arsenido Derivatives of Al and Ga. X-ray Structures of [t-Bu₂Ga(μ-OH)]₃ and [t-Bu₂Ga(μ-NH₂)]₃," D. A. Atwood, A. H. Cowley, P. R. Harris, R. A. Jones, S. U. Koschmieder, C. M. Nunn, J. L. Atwood and S. G. Bott, Organometallics, 1993, 12, 24-29.
- *23. "Monomeric Base-Stabilized Phosphino- and Arsinoalanes. A Quest for a New Aluminum Source," D. A. Atwood, L. Contreras, A. H. Cowley, R. A. Jones and M. A. Mardones, *Organometallics*. 1993, 12, 17-18.

- *24. "An Indium-Phosphorus Heterocubane as a New Type of Indium Phosphide Precursor," D. A. Atwood, A. H. Cowley, R. A. Jones and M. A. Mardones, J. Organomet. Chem. 1993, 449, C1-C2.
- *25. "Alkyl Amido Gallate Complexes of the Group I and II Elements," D. A. Atwood, A. H. Cowley and R. A. Jones, *Organometallics*. 1993, 12, 236-238.
- *26. "Synthesis and Characterization of Bridged Dimeric and Trimeric Group 13/15 Complexes Containing Primary Phosphido [(¹Bu)PH] and Arsenido [(¹BuAsH)] Units," D. A. Atwood, A. H. Cowley, P. R. Harris, R. A. Jones, S. U. Koschmieder and C. M. Nunn, J. Organomet. Chem. 1993, 449, 61-67.
- *27. "Use of the 2,4,6-Tris(trifluoromethyl)phenyl Ligand To Stabilize Indium-Indium and Gallium-Gallium Bonds," R. D. Schluter, A. H. Cowley, D. A. Atwood, R. A. Jones, M. R. Bond, and C. J. Carrano, J. Amer. Chem. Soc. 1993, 115, 2070-2071.

ACCEPTED

1. "Synthesis and Structural Characterization of a Homoleptic Bismuth Aryl Thiolate" D. A. Atwood, A. H. Cowley, R. D. Hernandez, R. A. Jones, L. L. Rand, S. G. Bott and J. L. Atwood, *Inorg. Chem.* Accepted.

SUBMITTED

- "Synthesis and Structures of [NMe₂(μ-NMe₂)GaCl]₂ and [TMP(μ-OEt)GaCl]₂ (TMP = 2,6 tetramethylpipyridine)," D. A. Atwood, A. H. Cowley, R. A. Jones, M. A. Mardones, J. L. Atwood and S. G. Bott, J. Coord. Chem. Submitted.
- 2. "Monomeric Arsinoboranes. The Question of Arsenic-Boron π-Bonding," C. J. Carrano, L. Contreras, R. A. Jones, and M. A. Mardones, J. Chem. Soc., Chem. Commun. Submitted.
- 3. "Chemical Beam Epitaxy and Characterization of GaAs from [Me₂Ga(μ-As-t-Bu₂)]₂ and [Et₂Ga(μ-As-t-Bu₂)]₂" J. E. Miller, and J. G. Ekerdt, *Chem. Mater.* Submitted.
- *4. "Synthesis and Structural Characterization of Novel Gallosilicates," D. A. Atwood, A. H. Cowley, R. A. Jones, J. L. Atwood, and S. G. Bott, *Chem. Comm.* Submitted.
- *5. "Dimeric Gallium and Indium Dialkylphosphido Complexes with Unusual Group 13/15 Stoichiometries," D. A. Atwood, V. O. Atwood, A. H. Cowley, H. R. Gobran, and R. A. Jones, *Organometallics*. Submitted.
- *6. "Short Ga.-H-N Distances in Gallium Amine and Amide Complexes," D. A. Atwood, V. O. Atwood, D. F. Carriker, A. H. Cowley, F. P. Gabbai, and R. A. Jones, J. Organomet. Chem. In press.

D. LIST OF ALL PARTICIPATING SCIENTIFIC PERSONNEL SHOWING ADVANCED DEGREES EARNED WHILE EMPLOYED ON THE PROJECT

Graduate Students Supported:

David A. Atwood Paul R. Harris Michael Jackson Vikas Lakhetia Miguel Mardones James E. Miller

Ph.D.'s Awarded:

David A. Atwood - "A Synthetic and Structural Study of Heavier Group 13 Complexes of Nitrogen"

Paul R. Harris - "Synthesis, Characterization & Application of Novel III/V and III/VI Organometallic Compounds"

James E. Miller - "Chemical Beam Epitaxy of GaAs Using Novel Single-Source Precursors"

John W. Nail - "Single Source Precursors for the III/V Semiconducting Materials: From Design to Deposition"

Ronald J. Powell - "A Study of the Chelating Ability of Tertiary Diphosphine Ligands at a Nickel (II) Center"

Lora L. Rand - "Synthesis, Characterization and Reactivity of Sterically Hindered Sulfido-, Selenido- and Tellurido- Transition Metal and Main Group Complexes"

Mark D. Soucek - "Stabilization of Metal Clusters with 1,2-Phenylene Linked Diphosphines"

August 2n For

Postdoc Supported:

Stefan U. Koschmieder

